

# ELECTRON SOURCE MANUFACTURING APPARATUS

## BACKGROUND OF THE INVENTION

### Field of the Invention

5       The present invention relates to an electron source manufacturing apparatus.

### Related Background Art

Conventionally, electron-emitting devices are mainly classified into two types of devices: thermionic  
10       cathodes and cold cathodes. The cold cathodes include a field emission type electron-emitting device, metal/insulator/metal type electron-emitting device, and surface conduction electron-emitting device.

15       The surface conduction electron-emitting device utilizes the phenomenon that electrons are emitted by flowing a current through a small-area thin film formed on a substrate parallel to the film surface. Many proposals have been made for a surface conduction electron-emitting device having a new structure and its  
20       applications. For example, a basic structure or manufacturing method is disclosed in Japanese Patent Application Laid-Open No. 7-235255.

Such an electron source and an image-forming apparatus using the electron source are manufactured as  
25       follows.

According to the first manufacturing method, an electron source substrate on which a plurality of units

0000504 062601

According to the second method, an electron source  
20 substrate on which a plurality of units each made up of  
a conductive film and a pair of device electrodes  
connected to the conductive film, and wiring lines  
connected to the plurality of units are laid out is  
formed. The obtained electron source substrate and a  
25 substrate bearing phosphors are bonded to each other  
via a support frame, forming the panel of an  
image-forming apparatus. Then, the "forming step" of

5 introducing organic substance-containing gas into the  
panel via the exhaust pipe and applying a voltage to  
each unit again via the external terminal under the  
organic substance-containing atmosphere to deposit  
carbon or a carbon compound near the gap is executed,  
0 thereby changing each unit into an electron-emitting  
device. The exhaust pipe connected to the panel is  
sealed, completing an image-forming apparatus.

15 Especially the first manufacturing method requires  
a larger-size vacuum chamber and higher-vacuum exhaust  
device as the electron source substrate becomes larger  
in size. The second manufacturing method takes a long  
time for evacuation from the internal space of the  
20 panel of the image-forming apparatus and introduction  
of organic substance-containing gas into the internal  
space of the panel.

It is an object of the present invention to provide an electron source manufacturing apparatus 25 which can be easily downsized and operated.

It is another object of the present invention to provide an electron source manufacturing method which

can increase the manufacturing speed and is suitable for mass production.

It is still another object of the present invention to provide an electron source manufacturing apparatus and manufacturing method capable of manufacturing an electron source excellent in electron emitting characteristics.

According to the present invention, there is provided an electron source manufacturing apparatus comprising a support which supports a substrate having a conductor formed thereon and has means for adjusting a temperature of the substrate, a vessel which has a gas inlet port and a gas exhaust port and covers part of the substrate, means for introducing and exhausting gas into and from the vessel, and means for applying a voltage to the conductor, wherein a gap or groove is formed at a predetermined portion of the support.

According to the present invention, there is provided an electron source manufacturing apparatus comprising a support which supports a substrate having a plurality of conductors each comprising a pair of electrodes and a conductive film formed between the electrodes, a vessel which covers part of the substrate, means for introducing and exhausting gas into and from a space defined by the vessel and the substrate, and means for applying a voltage to each conductor, wherein the support has a groove in a

surface in contact with the substrate.

The present invention achieves downsizing of the electron source manufacturing apparatus and high operability for electrical connection to a power supply or the like. In addition, the degree of freedom of design such as the size and shape of the vessel increases. Gas can be introduced/exhausted into/from the vessel within a short time, thus shortening the manufacturing time. The reproducibility and uniformity of the electron-emitting characteristics of a manufactured electron source can be improved.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1A, 1B and 1C are sectional views sequentially showing an operation in an embodiment of the present invention;

Fig. 2 is a sectional view showing an apparatus in the embodiment of the present invention;

Fig. 3 is a plan view showing an electron source substrate before formation of an electron emitting portion in the embodiment of the present invention;

Fig. 4 is a view showing a pipe and circuit in the embodiment of the present invention;

Fig. 5 is a view showing a control circuit in the embodiment of the present invention;

Fig. 6 is a plan view showing an electron source substrate having a plurality of devices in the

0088594-062604

embodiment of the present invention;

Fig. 7 is a partial sectional view showing the apparatus in the embodiment of the present invention;

Fig. 8 is a perspective view showing a support in  
5 the embodiment of the present invention;

Fig. 9 is a view showing Example 1 in the embodiment of the present invention;

Fig. 10 is a view showing Example 2 in the embodiment of the present invention;

Fig. 11 is a view showing Example 3 in the  
10 embodiment of the present invention;

Fig. 12 is a view showing Example 4 in the embodiment of the present invention;

Fig. 13 is a view showing a comparative example to  
15 the present invention; and

Fig. 14 is a table showing the results of the respective examples and comparative example in the present invention.

## 20 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Preferred embodiments of the present invention will be described in detail below with reference to the accompanying drawings.

Figs. 1A to 1C and 2 are schematic views showing  
25 an embodiment of the present invention. Figs. 1A to 1C are schematic views each showing the operation state of a manufacturing apparatus according to the present

00000000-00000000

invention. Fig. 2 is a schematic sectional view mainly showing the main building members of the manufacturing apparatus according to the present invention. Fig. 3 is a schematic view showing a substrate 1 on which a plurality of units (electrodes 19 and conductive films 18) before the "forming step" (to be described later), and wiring lines 20 and 21 connected to apply a voltage to the units are laid out. Fig. 4 is a schematic view mainly showing the piping circuits of the evacuation gas supply system and support driving system of the manufacturing apparatus according to the present invention. Fig. 5 is a view mainly showing the control circuits of the temperature adjustment system and power supply system of the manufacturing apparatus according to the present invention. Fig. 6 is a schematic view showing an electron source substrate having a plurality of electron-emitting devices manufactured by the manufacturing apparatus according to the present invention.

In the present invention, a member made up of a pair of electrodes and a conductive film which connects the electrodes will be referred to as a "conductor" or "unit". The "unit" ("conductor") undergoes the above-described "forming step" or the "forming step" and "activation step" to change the "unit" into an electron-emitting device.

In Figs. 1A to 1C and 2, the substrate 1 has

00000504-052501

5

10

15

20

25



perspective schematic view showing the support 9.

As shown in Fig. 7, the width of the groove 61 is defined by two ends in substantially contact with the substrate 1. The surface of the substrate 1 has  
5 concave and convex shape or warps, so the two ends need not always contact the substrate 1, as shown in Fig. 7.

One end inside the groove 61 is positioned more inward than the periphery of the region where units are laid out. The inner end is positioned more inward by 1  
10 mm or more than the periphery of the region where units are laid out. The inner end is preferably positioned more inward by 2 mm or more than the periphery of the region where units are laid out.

The other end outside the groove 61 is positioned  
15 more outward than the region where units are laid out. The outer end is positioned more outward by 10 mm or more than the periphery of the region where units are laid out. The outer end is positioned more inward than the periphery of the substrate 1.

The support 9 supports the electron source  
20 substrate 1 and adjusts its temperature. The support 9 comprises a fixing means such as a vacuum chuck mechanism or the electrostatic chuck 8 for fixing the electron source substrate 1, and a temperature control  
25 means such as the heating means 10 and/or cooling means 11 for keeping the electron source substrate 1 at a predetermined temperature.

0988504.062604

0988594, 052604

The temperature control means can keep the surface temperature of the electron source substrate 1 at a predetermined temperature in the "forming step" and "activation step". This means has a function of suppressing dehumidification from the surface of the substrate 1 and thermal variations in the electrical processing step ("forming step" and "activation step").

In the present invention, the temperature of the substrate 1 having conductors (units) is controlled in the "activation step" and/or "forming step". This temperature is controlled by the support 9.

If the temperature of the substrate 1 is not controlled, the substrate 1 may be damaged by Joule heat generated along with the "forming step" and "activation step" though it depends on the number of "units" and the material and thickness of the substrate 1. If the substrate 1 is not controlled to a proper temperature, gaps formed in respective units vary in shape, resulting in a low-uniformity electron source.

In the present invention, as shown in Figs. 7 and 8, the gap (groove) 61 is formed in a portion of the support 9 that corresponds to the periphery of the region where "units" are laid out, in order to suppress the temperature distribution at the periphery of the region where "units" are laid out. This structure can suppress dissipation of heat at the periphery of the region where units are laid out. As a result, a

5       The vessel 4 is made of stainless steel, titanium,  
or glass, and is desirably formed from a material which  
hardly discharges gas from the vessel. The vessel 4  
covers the region 2 of the substrate 1 where units are  
formed, and at least the interior of the vessel 4 can  
stand a pressure of  $1 \times 10^{-4}$  Pa to atmospheric pressure.  
0       Thus, the space defined by the vessel 4 and the  
substrate 1 having units can be maintained in a  
depressurized state.

The seal member 7 disposed at the joint portion between the vessel 4 and the substrate 1 holds the airtightness between the substrate 1 and the vessel 4, and is an O-ring or rubber sheet. The seal member 7 is in contact with the substrate 1 outside the region 2 where a plurality of units are laid out. Note that the seal member 7 is also in contact with the substrate 1 on the wiring lines 20 and 21 (see reference numeral 3 in Fig. 3).

As shown in Fig. 3, "extracted wiring lines" in the present invention are part (ends) of the wiring lines 20 and 21 for connecting units (each made up of the pair of electrodes 19 and the conductive film 18) to an external power supply, and are located in a

region (air-exposed region) outside the space defined by the vessel 4 and substrate 1.

5 The exhaust pipe 6 is connected to a vacuum pump 33 via a pipe shown in Fig. 4, and evacuates the space defined by the vessel 4 and substrate 1. The gas inlet pipe 5 is used to introduce predetermined gas into the space defined by the vessel 4 and substrate 1. The introduced gas includes an organic substance used for the "activation step" and hydrogen gas used for the "forming step".

10 The probes 12 are located outside the vessel 4, and are connected to wiring lines (extracted wiring lines) exposed to air. The extracted wiring lines are part of the wiring lines 20 and 21 in Fig. 3, and are particularly the wiring lines 20 and 21 at positions (outside the region 3) where they are exposed to air when the vessel 4 covers the substrate 1. The probes 12 are fixed to the probe unit 14, and the probe unit 14 has the camera 13 for alignment. The camera 13 reads the position of an alignment mark on the substrate 1, and the position of the probe unit 14 is aligned to the position of the substrate 1 so as to make the probes 12 reliably contact the extracted wiring lines exposed to air.

25 In Fig. 4, the manufacturing apparatus comprises a pipe 31, a valve 32, a vacuum pump 33, an activation gas supply pipe 34, an activation gas valve 35, an

0000504 062501  
102230 425860

activation gas cylinder 36, a forming gas supply pipe  
37, a forming gas supply valve 38, a forming gas  
cylinder 39, pipes 43 for chuck evacuation and gas  
introduction, a valve 44, a vacuum pump 45, a selector  
5 valve 46, a valve 47, a gas supply source 48 for helium  
gas or the like, a support elevation driving motor 49,  
a support elevation power transmission shaft 50, an  
electrical line 51 to the support elevation driving  
motor 49, and a support elevation driving motor  
10 controller 52.

In Fig. 5, the manufacturing apparatus comprises a  
sensor 71 for measuring the temperature of the support  
9, a temperature signal line 72, a heater controller  
73, a wiring line 74 which connects a heater and the  
15 heater controller 73, a cooling water supply controller  
75, a cooling water pipe 76, a valve 77, a voltage  
application source 78 to the electrostatic chuck, an  
elevation actuator 91 of the probe alignment unit, a  
probe alignment actuator 92, an actuator driving  
20 controller 95, wiring lines 93 and 94 which connect the  
actuators 91 and 92 to the actuator driving controller,  
a signal line 96 extending from the alignment mark  
reading camera 13, a driver 98, and a wiring line 97  
which connects the driver 98 to the probe 12.

25 An example of an electron source manufacturing  
method using the manufacturing apparatus with the above  
arrangement will be described with reference to

0000504.062601

Figs. 1A, 1B and 1C to Fig. 5.

The glass substrate 1 (Fig. 3) whose surface has a plurality of conductors (units each made up of the conductive film 18 and the pair of electrodes 19) and the X- and Y-direction wiring lines 20 and 21 connected to the conductors is set on the support 9.

The conductive film is a thin film made of a conductive material such as Ni, Au, PdO, Pd, or Pt. In Fig. 3, the seal member 7 disposed between the vessel 4 and the substrate 1 is in contact with the substrate 1 in the region 3.

The temperature sensor 71 measures the temperature near the surface of the support 9, and the heater controller 73 and heating means 10 control the temperature of the support 9 so as to adjust it to a desired temperature (first temperature).

At this time, the valves 44 and 46 are opened, and the valve 47 is closed. The substrate 1 is vacuum-chucked from the vacuum chuck holes 15 via the pipes 43, and tightly contacts the surface of the support 9. The electrostatic chuck 8 receives a voltage from the voltage application source 78, and the substrate 1 is electrostatically chucked to the surface of the electrostatic chuck (Fig. 1A).

The support elevation driving motor controller 52 supplies a signal to the support elevation driving motor 49, and the support elevation power transmission

0988594.062604

shaft 50 moves up the support 9. When the support 9 moves up, the upper surface of the substrate 1 comes into contact with the seal member 7 of the vessel 4 (Fig. 1B).

5       The probes 12 and the wiring lines 20 and 21 are connected as follows.

          The alignment camera 13 reads an alignment mark on the surface of the substrate 1, and the actuator driving controller 95 calculates the positions of  
10       extracted wiring lines on the substrate 1. Based on the calculated values, the actuator driving controller 95 moves the probe alignment actuator 92 via the actuator wiring line 94. The position of the alignment unit is adjusted in the X and Y directions so as to  
15       position the distal ends of the probes 12 onto the extracted wiring lines.

          A signal is sent to the elevation actuator 91 of the probe alignment unit, the probe unit moves down in the Z direction, and the extracted wiring lines and the  
20       distal ends of the probes 12 come into contact with each other.

          The evacuation valve 32 is opened, and the vacuum pump 33 evacuates the space defined by the vessel 4 and substrate 1 to a desired vacuum degree (e.g.,  $1 \times 10^{-4}$   
25       Pa or more) via the pipe 31 connected to the exhaust pipe 6.

          When the conductive film is made of an oxide, the

0000594-062604

5

10

15

20

25



temperature of the support 9 is set to one set in the forming step.

Then, the "activation step" is performed by starting voltage application to respective units via the X- and Y-direction wiring lines 20 and 21 from the probes 12 using the driver 98. By the "activation step", a carbon film is formed in the gap formed by the "forming step" and on the conductive film near the gap. The "activation step" ends when a current flowing through a pair of electrodes which constitute each unit reaches a desired value.

By this step, each unit changes into an electron-emitting device, completing an electron source substrate (Fig. 6).

During the "activation step", the heater controller 73 and the heating means 10 or cooling means 11 control the temperature of the support 9 so as to adjust it to a desired temperature (second temperature) while the temperature sensor 71 measures the surface temperature of the support 9.

After the "activation step", the probes 12 are moved apart from the extracted wiring lines. The activation gas valve 35 is closed, and the activation gas in the vessel is exhausted.

The support elevation driving motor controller 52 supplies a signal to the support elevation driving motor 49, and the support elevation power transmission

10888594.082501

shaft 50 moves down the support 9 to move the substrate 1 apart from the seal member 7 of the vessel 4.

Finally, the electron source substrate 1 having many electron-emitting devices is extracted from the surface of the support 9.

The electron source substrate 1 manufactured by using the above-described apparatus shown in Fig. 7, and a face plate having phosphors and anode electrodes are sealed via a frame member and spacers with a bonding agent such as frit glass, thereby completing an image-forming apparatus.

In the present invention, if the "forming step" and "activation step" are executed while the probes 12 are in contact with the extracted wiring lines of the substrate 1, each unit (conductor) generates heat. If Joule heat generated by each unit during the "forming step" or "activation step" varies, the electron-emitting characteristics of formed electron-emitting devices vary or are adversely affected. To prevent this, the surface temperature of the substrate 1 must be held as constant as possible. In the present invention, therefore, the temperature of the substrate 1 is controlled by controlling that of the support 9 in the "forming step" and "activation step".

In the present invention, the temperatures of the substrate 1 and support 9 are adjusted lower than a set

00000004.002501

5 "activation step" starts. At the same time, the temperature of the support 9 is controlled to adjust that of the substrate 1 to the first or second temperature.

This manufacturing process of the present invention can suppress misalignment between the relative positions of the extracted wiring line of the substrate 1 and the distal end of the probe 12 in the "forming step" and "activation step".

If the extracted wiring lines are brought into contact with the probes 12 at room temperature without adjusting the temperature of the substrate 1 by the above method, and the "forming step" or "activation step" is performed while the temperature is controlled, the relative positions of the extracted wiring line of the substrate 1 and the distal end of the probe 12 may be misaligned owing to thermal expansion or contraction of the substrate 1. With a large misalignment amount, the probes 12 may move apart from the extracted wiring lines, failing in the "forming step" or "activation step".

However, the manufacturing process of the present invention can suppress variations in the relative

positions of the probe and extracted wiring line caused by changes in shape along with thermal expansion or contraction of the substrate 1. As a result, a high-uniformity electron-emitting device and electron source can be stably formed.

The manufacturing method using the manufacturing apparatus of the present invention can greatly shorten the time taken for the "forming step" and "activation step" and can easily form a high-uniformity electron source and image-forming apparatus.

(Example 1)

In Example 1, the size of a gap 61 formed in a support 9 (side of an electrostatic chuck 8) was defined by an outer side corresponding to 15 mm from the outside and an inner side corresponding to 1 mm inward from the periphery of a region 2 where a plurality of units were formed, as shown in Fig. 9.

With this electron source manufacturing apparatus, the temperature distribution of the region where a plurality of units were formed was 9.5°C during the "activation step", and a high-uniformity electron-emitting device was manufactured.

(Example 2)

In Example 2, the schematic arrangement and components of the apparatus were the same as those in Example 1. The size of a gap 61 formed in an electrostatic chuck 8 was defined by an outer side

09080504-062604

corresponding to 15 mm from the outside and an inner side corresponding to 2 mm inward from the periphery of a region 2 where a plurality of units were formed, as shown in Fig. 10.

5           With this electron source manufacturing apparatus, the temperature distribution of the region where a plurality of units were formed was 6.2°C during the "activation step", as shown in Fig. 10. The uniformity of the electron-emitting characteristics of the  
10   electron source substrate manufactured in Example 2 was equal to or higher than that in Example 1.  
(Example 3)

          In Example 3, the schematic arrangement and components of the apparatus were the same as those in  
15   Example 1. The size of a gap 61 formed in an electrostatic chuck 8 was defined by an outer side corresponding to 25 mm from the outside and an inner side corresponding to 1 mm inward from the periphery of a region 2 where a plurality of units were formed, as  
20   shown in Fig. 11.

          With this electron source manufacturing apparatus, the temperature distribution of the region where a plurality of units were formed was 9.1°C during the "activation step", as shown in Fig. 11. The uniformity  
25   of the electron-emitting characteristics of the electron source substrate manufactured in Example 3 was equal to or higher than that in Example 1.

00000594.062601



(Comparative Example)

In the comparative example, the schematic arrangement and components of the apparatus were the same as those in Example 1. As shown in Fig. 13, no gap was formed in a support 9 (side of an electrostatic chuck 8).

With this electron source manufacturing apparatus, the temperature distribution of the region where a plurality of units were formed was 19.1°C during the "activation step", as shown in Fig. 13. The uniformity of the electron source substrate was lower than that of the electron source substrate formed in Example 1. The electron source manufactured by using the apparatus of the comparative example may lose the electrical contact between a probe 12 and an extracted wiring line due to deformation of the substrate.

Fig. 14 shows the results of the respective examples and comparative example.

As has been described above, the present invention can provide an electron source manufacturing apparatus which can be easily downsized and operated. The present invention can provide an electron source manufacturing method which can increase the manufacturing speed and is suitable for mass production. The present invention can provide an electron source manufacturing apparatus and manufacturing method capable of manufacturing an

0988504-062504

electron source excellent in electron-emitting characteristics. Furthermore, the present invention can provide an image-forming apparatus excellent in image quality.

0988594-062601